Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2018-05-05-04** **Date: 10/05/2018**

Customer : Assistant Executive Engineer, Vidyaranyapura Sub Division, Bangalore

Address : Vidyaranyapura Sub Division, Bangalore

Project Name : Package No. 04 (Package consists of 28 works)

Agency : M/s. Ram and company, Sri. C R GIRISH, No. 12, Patel Pillegowda layout, Ramachandrapura, Bangalore- 560013

Customer's Reference : BBMP/EE/BTP/WO/129/2017-18

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 05-05-18

Sample ID No : 2018-05-05-04 /01

Customer ID : M30 Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M30 / 7 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 10/05/2018

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	M30 Concrete	M30	03/05/2018	10/05/2018	150.22 X 149.61 X 150.67	22474	8.388	567.6	25.3	25.6
2	M30 Concrete	M30	03/05/2018	10/05/2018	150.61 X 149.11 X 151.61	22457	8.301	606.1	27.0	
3	M30 Concrete	M30	03/05/2018	10/05/2018	151.41 X 151.15 X 151.89	22885	8.116	561.8	24.5	

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

Assistant Executive Engineer
Vidyaranyapura Sub Division
BBMP, Bangalore-97

CIVIL Pro Sig. Date BANGALORE

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL |
GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2018-05-05-04** **Date: 31/05/2018**

Customer : Assistant Executive Engineer, Vidyaranyapura Sub Division, Bangalore

Address : Vidyaranyapura Sub Division, Bangalore

Project Name : Package No. 04 (Package consists of 28 works)

Agency : M/s. Ram and company, Sri. C R GIRISH, No. 12, Patel Pillegowda layout, Ramachandrapura, Bangalore-560013

Customer's Reference : BBMP/EE/BTP/WO/129/2017-18

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 05-05-18

Sample ID No : 2018-05-05-04 /02

Customer ID : M30 Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M30 / 28 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 31/05/2018

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	M30 Concrete	M30	03/05/2018	31/05/2018	150.51 X 151.41 X 151.93	22789	8.249	772.5	33.9	33.3
2	M30 Concrete	M30	03/05/2018	31/05/2018	150.96 X 149.72 X 149.66	22601	8.260	744.0	32.9	
3	M30 Concrete	M30	03/05/2018	31/05/2018	150.35 X 151.06 X 150.77	22712	8.202	752.8	33.1	

Note:
The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

Assistant Executive Engineer
Vidyaranyapura Sub Division
BBMP, Bangalore - 97

CIVIL Pro Sig..... Date..... BANGALORE

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL | GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2018-05-08-03** **Date: 12/05/2018**

Customer : Assistant Executive Engineer, Vidyaranyapura Sub Division, Bangalore

Address : Vidyaranyapura Sub Division, Bangalore

Project Name : Package No. 04 (Package consists of 28 works)

Agency : M/s. Ram and company, Sri. C R GIRISH, No. 12, Patel Pillegowda layout, Ramachandrapura, Bangalore- 560013

Customer's Reference : BBMP/EE/BTP/WO/129/2017-18

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 08-05-18

Sample ID No : 2018-05-08-03 /01

Customer ID : M30 Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M30 / 7 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 12/05/2018

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	M30 Concrete	M30	05/05/2018	12/05/2018	150.67 X 150.88 X 150.90	22734	8.238	583.1	25.7	25.6
2	M30 Concrete	M30	05/05/2018	12/05/2018	149.18 X 149.86 X 149.64	22357	8.329	594.6	26.6	
3	M30 Concrete	M30	05/05/2018	12/05/2018	149.80 X 149.65 X 149.04	22417	8.242	547.4	24.4	

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

Assistant Executive Engineer
Vidyaranyapura Sub Division
BBMP, Bangalore - 97

CIVIL Pro Sig..... Date..... BANGALORE

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL |
GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2018-05-08-03** **Date: 02/06/2018**

Customer : Assistant Executive Engineer, Vidyaranyapura Sub Division, Bangalore

Address : Vidyaranyapura Sub Division, Bangalore

Project Name : Pacakage No. 04 (Package consists of 28 works)

Agency : M/s. Ram and company, Sri. C R GIRISH, No. 12, Patel Pillegowda layout, Ramachandrapura, Bangalore-560013

Customer's Reference : BBMP/EE/BTP/WO/129/2017-18

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 08-05-18

Sample ID No : 2018-05-08-03 /02

Customer ID : M30 Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M30 / 28 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 02/06/2018

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	M30 Concrete	M30	05/05/2018	02/06/2018	149.27 X 151.97 X 150.36	22685	8.485	765.3	33.7	33.4
2	M30 Concrete	M30	05/05/2018	02/06/2018	151.08 X 150.06 X 149.55	22671	8.172	744.0	32.8	
3	M30 Concrete	M30	05/05/2018	02/06/2018	150.25 X 150.07 X 149.20	22548	8.541	758.3	33.6	

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

Assistant Executive Engineer
Vidyaranyapura Sub Division
BBMP, Bangalore - 97

CIVIL Pro Sig..... Date..... BANGALORE

****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2018-05-07-06** **Date: 11/05/2018**

Customer : Assistant Executive Engineer, Vidyaranyapura Sub Division, Bangalore

Address : Vidyaranyapura Sub Division, Bangalore

Project Name : Package No. 04 (Package consists of 28 works)

Agency : M/s. Ram and company, Sri. C R GIRISH, No. 12, Patel Pillegowda layout, Ramachandrapura, Bangalore- 560013

Customer's Reference : BBMP/EE/BTP/WO/129/2017-18

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 07-05-18

Sample ID No : 2018-05-07-06 /01

Customer ID : M30 Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M30 / 7 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 11/05/2018

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	M30 Concrete	M30	04/05/2018	11/05/2018	151.02 X 151.94 X 149.86	22947	8.301	584.3	25.5	25.3
2	M30 Concrete	M30	04/05/2018	11/05/2018	149.18 X 150.88 X 149.42	22508	8.385	592.0	26.3	
3	M30 Concrete	M30	04/05/2018	11/05/2018	149.37 X 149.48 X 151.27	22328	8.348	541.3	24.2	

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

Assistant Executive Engineer
Vidyaranyapura Sub Division
BBMP, Bangalore - 97

CIVIL Pro Sig Date BANGALORE

Page 1/1
****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2018-05-07-06** **Date: 01/06/2018**

Customer : Assistant Executive Engineer, Vidyaranyapura Sub Division, Bangalore

Address : Vidyaranyapura Sub Division, Bangalore

Project Name : Pacakage No. 04 (Package consists of 28 works)

Agency : M/s. Ram and company, Sri. C R GIRISH, No. 12, Patel Pillegowda layout, Ramachandrapura, Bangalore-560013

Customer's Reference : BBMP/EE/BTP/WO/129/2017-18

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 07-05-18

Sample ID No : 2018-05-07-06 /02

Customer ID : M30 Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M30 / 28 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 01/06/2018

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	M30 Concrete	M30	04/05/2018	01/06/2018	150.58 X 150.70 X 150.10	22694	8.542	750.0	33.1	32.8
2	M30 Concrete	M30	04/05/2018	01/06/2018	149.37 X 151.88 X 151.64	22686	8.209	731.1	32.2	
3	M30 Concrete	M30	04/05/2018	01/06/2018	149.81 X 149.24 X 151.11	22357	8.448	742.7	33.2	

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

Assistant Executive Engineer
Vidyaranyapura Sub Division
BBMP, Bangalore-92

CIVIL Pro BANGALORE Sig Date

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL | GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2018-05-21-03** **Date: 25/05/2018**

Customer : Assistant Executive Engineer, Vidyaranyapura Sub Division, Bangalore

Address : Vidyaranyapura Sub Division, Bangalore

Project Name : Package No. 04 (Package consists of 28 works)

Agency : M/s. Ram and company, Sri. C R GIRISH, No. 12, Patel Pillegowda layout, Ramachandrapura, Bangalore- 560013

Customer's Reference : BBMP/EE/BTP/WO/129/2017-18

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 21-05-18

Sample ID No : 2018-05-21-03 /01

Customer ID : M30 Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M30 / 7 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 25/05/2018

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	M30 Concrete	M30	18/05/2018	25/05/2018	150.70 X 150.04 X 149.53	22611	8.267	567.0	25.1	25.4
2	M30 Concrete	M30	18/05/2018	25/05/2018	151.91 X 150.17 X 150.12	22813	8.363	611.3	26.8	
3	M30 Concrete	M30	18/05/2018	25/05/2018	149.90 X 149.18 X 149.08	22362	8.499	545.6	24.4	

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

Assistant Executive Engineer
Vidyaranyapura Sub Division
BBMP, Bangalore - 97

CIVIL Pro Sig..... Date..... BANGALORE

Page 1/1
****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2018-05-21-03** **Date: 15/06/2018**

Customer : Assistant Executive Engineer, Vidyaranyapura Sub Division, Bangalore

Address : Vidyaranyapura Sub Division, Bangalore

Project Name : Pacakage No. 04 (Package consists of 28 works)

Agency : M/s. Ram and company, Sri. C R GIRISH, No. 12, Patel Pillegowda layout, Ramachandrapura, Bangalore-560013

Customer's Reference : BBMP/EE/BTP/WO/129/2017-18

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 21-05-18

Sample ID No : 2018-05-21-03 /02

Customer ID : M30 Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M30 / 28 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 15/06/2018

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	M30 Concrete	M30	18/05/2018	15/06/2018	151.88 X 151.64 X 150.82	23031	8.075	782.3	34.0	33.4
2	M30 Concrete	M30	18/05/2018	15/06/2018	151.05 X 151.49 X 149.95	22882	8.230	737.1	32.2	
3	M30 Concrete	M30	18/05/2018	15/06/2018	151.25 X 150.06 X 149.77	22697	7.984	770.2	33.9	

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

Assistant Executive Engineer
Vidyaranyapura Sub Division
BBMP, Bangalore - 97

CIVIL Pro Sig Date BANGALORE

Page 1/1
****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID	:	**CP-2018-05-17-03** **Date: 22/05/2018**
Customer	:	Assistant Executive Engineer, Vidyaranyapura Sub Division, Bangalore
Address	:	Vidyaranyapura Sub Division, Bangalore
Project Name	:	Package No. 04 (Package consists of 28 works)
Agency	:	M/s. Ram and company, Sri. C R GIRISH, No. 12, Patel Pillegowda layout, Ramachandrapura, Bangalore- 560013
Customer's Reference	:	BBMP/EE/BTP/WO/129/2017-18
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	17-05-18
Sample ID No	:	2018-05-17-03 /01
Customer ID	:	M30 Concrete
Sample Type /Size	:	150X150X150 mm
Sample grade/Age	:	M30 / 7 Days Compressive Strength
Reference to BIS codes	:	IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5
Date of test	:	22/05/2018

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	M30 Concrete	M30	15/05/2018	22/05/2018	151.78 X 150.39 X 151.65	22827	8.103	578.5	25.3	25.4
2	M30 Concrete	M30	15/05/2018	22/05/2018	151.97 X 149.04 X 150.29	22650	8.339	595.1	26.3	
3	M30 Concrete	M30	15/05/2018	22/05/2018	151.93 X 149.02 X 151.11	22641	8.531	555.3	24.5	

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

Assistant Executive Engineer
Vidyaranyapura Sub Division
BBMP, Bangalore - 97

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

Page 1/1
****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2018-05-17-03** **Date: 12/06/2018**

Customer : Assistant Executive Engineer, Vidyaranyapura Sub Division, Bangalore

Address : Vidyaranyapura Sub Division, Bangalore

Project Name : Pacakage No. 04 (Package consists of 28 works)

Agency : M/s. Ram and company, Sri. C R GIRISH, No. 12, Patel Pillegowda layout, Ramachandrapura, Bangalore-560013

Customer's Reference : BBMP/EE/BTP/WO/129/2017-18

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 17-05-18

Sample ID No : 2018-05-17-03 /02

Customer ID : M30 Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M30 / 28 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 12/06/2018

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	M30 Concrete	M30	15/05/2018	12/06/2018	151.12 X 150.60 X 150.86	22758	8.315	755.6	33.2	32.7
2	M30 Concrete	M30	15/05/2018	12/06/2018	151.61 X 149.11 X 150.72	22607	8.402	724.0	32.0	
3	M30 Concrete	M30	15/05/2018	12/06/2018	149.30 X 149.97 X 151.30	22391	8.239	739.4	33.0	

Note:
The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

Assistant Executive Engineer
Vidyaranyapura Sub Division
BBMP, Bangalore - 97

Page 1/1
****End of Report****

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.
R KARTHIK RECHAN
Authorized Signatory
Quality Manager

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2018-05-16-03** **Date: 21/05/2018**

Customer : Assistant Executive Engineer, Vidyaranyapura Sub Division, Bangalore

Address : Vidyaranyapura Sub Division, Bangalore

Project Name : Package No. 04 (Package consists of 28 works)

Agency : M/s. Ram and company, Sri. C R GIRISH, No. 12, Patel Pillegowda layout, Ramachandrapura, Bangalore- 560013

Customer's Reference : BBMP/EE/BTP/WO/129/2017-18

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 16-05-18

Sample ID No : 2018-05-16-03 /01

Customer ID : M30 Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M30 / 7 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 21/05/2018

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	M30 Concrete	M30	14/05/2018	21/05/2018	149.59 X 151.90 X 150.65	22723	8.349	570.6	25.1	25.4
2	M30 Concrete	M30	14/05/2018	21/05/2018	150.90 X 149.45 X 151.12	22553	8.198	592.4	26.3	
3	M30 Concrete	M30	14/05/2018	21/05/2018	149.88 X 150.52 X 151.82	22561	8.038	556.8	24.7	

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

Assistant Executive Engineer
Vidyaranyapura Sub Division
BBMP, Bangalore - 97

Page 1/1
****End of Report****

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2018-05-16-03** **Date: 11/06/2018**

Customer : Assistant Executive Engineer, Vidyaranyapura Sub Division, Bangalore

Address : Vidyaranyapura Sub Division, Bangalore

Project Name : Pacakage No. 04 (Package consists of 28 works)

Agency : M/s. Ram and company, Sri. C R GIRISH, No. 12, Patel Pillegowda layout, Ramachandrapura, Bangalore-560013

Customer's Reference : BBMP/EE/BTP/WO/129/2017-18

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 16-05-18

Sample ID No : 2018-05-16-03 /02

Customer ID : M30 Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M30 / 28 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 11/06/2018

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	M30 Concrete	M30	14/05/2018	11/06/2018	149.09 X 151.82 X 150.79	22635	8.203	755.5	33.4	33.3
2	M30 Concrete	M30	14/05/2018	11/06/2018	151.72 X 149.89 X 150.80	22741	8.337	746.7	32.8	
3	M30 Concrete	M30	14/05/2018	11/06/2018	150.69 X 149.84 X 151.43	22579	8.119	761.6	33.7	

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

CIVIL PRO Sig..... Date..... BANGALORE

Assistant Executive Engineer
Vidyaranyapura Sub Division
BBMP, Bangalore - 97

Page 1/1
****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : CP-2018-05-23-04 **Date: 28/05/2018**

Customer : Assistant Executive Engineer, Vidyaranyapura Sub Division, Bangalore

Address : Vidyaranyapura Sub Division, Bangalore

Project Name : Package No. 04 (Package consists of 28 works)

Agency : M/s. Ram and company, Sri. C R GIRISH, No. 12, Patel Pillegowda layout, Ramachandrapura, Bangalore- 560013

Customer's Reference : BBMP/EE/BTP/WO/129/2017-18

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 23-05-18

Sample ID No : 2018-05-23-04 /01

Customer ID : M30 Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M30 / 7 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 28/05/2018

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	M30 Concrete	M30	21/05/2018	28/05/2018	149.37 X 149.43 X 149.01	22320	8.233	579.2	25.9	25.7
2	M30 Concrete	M30	21/05/2018	28/05/2018	149.02 X 149.47 X 149.76	22274	8.120	590.5	26.5	
3	M30 Concrete	M30	21/05/2018	28/05/2018	151.55 X 150.50 X 149.29	22808	8.025	562.8	24.7	

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

Assistant Executive Engineer
Vidyaranyapura Sub Division
BBMP, Bangalore - 97

CIVIL Pro Sig..... Date..... BANGALORE

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL | GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID	:	**CP-2018-05-23-04** **Date: 18/06/2018**
Customer	:	Assistant Executive Engineer, Vidyaranyapura Sub Division, Bangalore
Address	:	Vidyaranyapura Sub Division, Bangalore
Project Name	:	Pacakage No. 04 (Package consists of 28 works)
Agency	:	M/s. Ram and company, Sri. C R GIRISH, No. 12, Patel Pillegowda layout, Ramachandrapura, Bangalore-560013
Customer's Reference	:	BBMP/EE/BTP/WO/129/2017-18
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	23-05-18
Sample ID No	:	2018-05-23-04 /02
Customer ID	:	M30 Concrete
Sample Type /Size	:	150X150X150 mm
Sample grade/Age	:	M30 / 28 Days Compressive Strength
Reference to BIS codes	:	IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5
Date of test	:	18/06/2018

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	M30 Concrete	M30	21/05/2018	18/06/2018	151.18 X 150.77 X 151.97	22794	8.350	758.2	33.3	33.3
2	M30 Concrete	M30	21/05/2018	18/06/2018	149.76 X 150.71 X 149.51	22570	8.052	744.3	33.0	
3	M30 Concrete	M30	21/05/2018	18/06/2018	150.95 X 150.75 X 150.49	22755	8.534	765.8	33.7	

Note:
The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

Assistant Executive Engineer
Vidyaranyapura Sub Division
BBMP, Bangalore - 97

CIVIL Pro Sig..... Date..... BANGALORE

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL |
GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2018-05-24-02** **Date: 29/05/2018**

Customer : Assistant Executive Engineer, Vidyaranyapura Sub Division, Bangalore

Address : Vidyaranyapura Sub Division, Bangalore

Project Name : Package No. 04 (Package consists of 28 works)

Agency : M/s. Ram and company, Sri. C R GIRISH, No. 12, Patel Pillegowda layout, Ramachandrapura, Bangalore- 560013

Customer's Reference : BBMP/EE/BTP/WO/129/2017-18

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 24-05-18

Sample ID No : 2018-05-24-02 /01

Customer ID : M30 Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M30 / 7 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 29/05/2018

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	M30 Concrete	M30	22/05/2018	29/05/2018	149.40 X 149.73 X 149.79	22370	8.110	576.9	25.8	25.7
2	M30 Concrete	M30	22/05/2018	29/05/2018	151.88 X 150.58 X 149.94	22870	8.285	614.3	26.9	
3	M30 Concrete	M30	22/05/2018	29/05/2018	151.44 X 151.20 X 149.35	22898	8.504	561.5	24.5	

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

Assistant Executive Engineer
Vidyaranyapura Sub Division
BBMP, Bangalore - 97

CIVIL Pro Sig..... Date..... BANGALORE

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL |
GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2018-05-24-02** **Date: 19/06/2018**

Customer : Assistant Executive Engineer, Vidyaranyapura Sub Division, Bangalore

Address : Vidyaranyapura Sub Division, Bangalore

Project Name : Pacakage No. 04 (Package consists of 28 works)

Agency : M/s. Ram and company, Sri. C R GIRISH, No. 12, Patel Pillegowda layout, Ramachandrapura, Bangalore-560013

Customer's Reference : BBMP/EE/BTP/WO/129/2017-18

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 24-05-18

Sample ID No : 2018-05-24-02 /02

Customer ID : M30 Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M30 / 28 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 19/06/2018

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	M30 Concrete	M30	22/05/2018	19/06/2018	150.52 X 150.68 X 150.50	22681	8.497	758.7	33.4	33.4
2	M30 Concrete	M30	22/05/2018	19/06/2018	151.44 X 151.74 X 150.22	22978	8.567	756.3	32.9	
3	M30 Concrete	M30	22/05/2018	19/06/2018	150.15 X 149.98 X 151.82	22520	8.309	759.8	33.7	

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

Assistant Executive Engineer
Vidyaranyapura Sub Division
BBMP, Bangalore - 97

CIVIL Pro Sig..... Date..... BANGALORE

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2018-04-20-05** **Date: 25/04/2018**

Customer : Assistant Executive Engineer, Vidyaranyapura Sub Division, Bangalore

Address : Vidyaranyapura Sub Division, Bangalore

Project Name : Package No. 04 (Package consists of 28 works)

Agency : M/s. Ram and company, Sri. C R GIRISH, No. 12, Patel Pillegowda layout, Ramachandrapura, Bangalore- 560013

Customer's Reference : BBMP/EE/BTP/WO/129/2017-18

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 20-04-18

Sample ID No : 2018-04-20-05 /01

Customer ID : M30 Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M30 / 7 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 25/04/2018

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	M30 Concrete	M30	18/04/2018	25/04/2018	151.05 X 150.58 X 149.04	22745	8.193	586.7	25.8	25.6
2	M30 Concrete	M30	18/04/2018	25/04/2018	150.07 X 151.56 X 151.17	22744	8.484	601.7	26.5	
3	M30 Concrete	M30	18/04/2018	25/04/2018	149.53 X 151.05 X 149.89	22586	8.418	556.9	24.7	

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

Assistant Executive Engineer
Vidyaranyapura Sub Division
BBMP, Bangalore - 97

FOR CIVIL Pro.

CIVIL Pro Sig..... Date..... BANGALORE

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

Page 1/1
****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID	:	**CP-2018-04-20-05** **Date: 16/05/2018**
Customer	:	Assistant Executive Engineer, Vidyaranyapura Sub Division, Bangalore
Address	:	Vidyaranyapura Sub Division, Bangalore
Project Name	:	Pacakage No. 04 (Package consists of 28 works)
Agency	:	M/s. Ram and company, Sri. C R GIRISH, No. 12, Patel Pillegowda layout, Ramachandrapura, Bangalore-560013
Customer's Reference	:	BBMP/EE/BTP/WO/129/2017-18
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	20-04-18
Sample ID No	:	2018-04-20-05 /02
Customer ID	:	M30 Concrete
Sample Type /Size	:	150X150X150 mm
Sample grade/Age	:	M30 / 28 Days Compressive Strength
Reference to BIS codes	:	IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5
Date of test	:	16/05/2018

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	M30 Concrete	M30	18/04/2018	16/05/2018	151.24 X 151.32 X 149.05	22885	8.503	772.6	33.8	33.5
2	M30 Concrete	M30	18/04/2018	16/05/2018	151.95 X 151.70 X 149.18	23050	7.978	757.1	32.8	
3	M30 Concrete	M30	18/04/2018	16/05/2018	149.35 X 149.25 X 150.98	22290	8.097	753.6	33.8	

Note:
The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

Assistant Executive Engineer
Vidyaranyapura Sub Division
BBMP, Bangalore - 97

CIVIL Pro Sig..... Date..... BANGALORE

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL |
GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2018-04-30-08** **Date: 05/05/2018**

Customer : Assistant Executive Engineer, Vidyaranyapura Sub Division, Bangalore

Address : Vidyaranyapura Sub Division, Bangalore

Project Name : Package No. 04 (Package consists of 28 works)

Agency : M/s. Ram and company, Sri. C R GIRISH, No. 12, Patel Pillegowda layout, Ramachandrapura, Bangalore- 560013

Customer's Reference : BBMP/EE/BTP/WO/129/2017-18

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 30-04-18

Sample ID No : 2018-04-30-08 /01

Customer ID : M30 Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M30 / 7 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 05/05/2018

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	M30 Concrete	M30	28/04/2018	05/05/2018	150.61 X 151.07 X 149.28	22754	8.120	579.7	25.5	25.5
2	M30 Concrete	M30	28/04/2018	05/05/2018	150.96 X 150.94 X 150.93	22786	8.345	600.8	26.4	
3	M30 Concrete	M30	28/04/2018	05/05/2018	150.16 X 149.97 X 149.37	22519	8.314	553.3	24.6	

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

Assistant Executive Engineer
Vidyaranyapura Sub Divisior
BBMP, Bangalore - 97

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

CIVIL Pro Sig..... Date..... BANGALORE

Page 1/1
****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2018-04-30-08** **Date: 26/05/2018**

Customer : Assistant Executive Engineer, Vidyaranyapura Sub Division, Bangalore

Address : Vidyaranyapura Sub Division, Bangalore

Project Name : Pacakage No. 04 (Package consists of 28 works)

Agency : M/s. Ram and company, Sri. C R GIRISH, No. 12, Patel Pillegowda layout, Ramachandrapura, Bangalore-560013

Customer's Reference : BBMP/EE/BTP/WO/129/2017-18

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 30-04-18

Sample ID No : 2018-04-30-08 /02

Customer ID : M30 Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M30 / 28 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 26/05/2018

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	M30 Concrete	M30	28/04/2018	26/05/2018	149.63 X 149.59 X 152.00	22383	8.380	755.6	33.8	33.2
2	M30 Concrete	M30	28/04/2018	26/05/2018	150.08 X 149.99 X 150.21	22511	8.322	725.1	32.2	
3	M30 Concrete	M30	28/04/2018	26/05/2018	149.50 X 149.15 X 151.22	22298	8.201	752.6	33.8	

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

Assistant Executive Engineer
Vidyaranyapura Sub Division
BBMP, Bangalore - 97

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

CIVIL Pro Sig..... Date..... BANGALORE

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL |
GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2018-05-14-04** **Date: 18/05/2018**

Customer : Assistant Executive Engineer, Vidyaranyapura Sub Division, Bangalore

Address : Vidyaranyapura Sub Division, Bangalore

Project Name : Package No. 04 (Package consists of 28 works)

Agency : M/s. Ram and company, Sri. C R GIRISH, No. 12, Patel Pillegowda layout, Ramachandrapura, Bangalore- 560013

Customer's Reference : BBMP/EE/BTP/WO/129/2017-18

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 14-05-18

Sample ID No : 2018-05-14-04 /01

Customer ID : M30 Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M30 / 7 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 18/05/2018

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	M30 Concrete	M30	11/05/2018	18/05/2018	151.99 X 151.37 X 149.17	23006	8.404	588.0	25.6	25.6
2	M30 Concrete	M30	11/05/2018	18/05/2018	149.71 X 151.95 X 150.62	22749	8.129	611.4	26.9	
3	M30 Concrete	M30	11/05/2018	18/05/2018	151.48 X 149.94 X 151.38	22712	8.552	556.8	24.5	

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

Assistant Executive Engineer
Vidyaranyapura Sub Division
BBMP, Bangalore - 97

CIVIL PRO Sig..... Date..... BANGALORE

Page 1/1
****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2018-05-14-04** **Date: 08/06/2018**

Customer : Assistant Executive Engineer, Vidyaranyapura Sub Division, Bangalore

Address : Vidyaranyapura Sub Division, Bangalore

Project Name : Pacakage No. 04 (Package consists of 28 works)

Agency : M/s. Ram and company, Sri. C R GIRISH, No. 12, Patel Pillegowda layout, Ramachandrapura, Bangalore-560013

Customer's Reference : BBMP/EE/BTP/WO/129/2017-18

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 14-05-18

Sample ID No : 2018-05-14-04 /02

Customer ID : M30 Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M30 / 28 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 08/06/2018

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	M30 Concrete	M30	11/05/2018	08/06/2018	151.92 X 151.10 X 149.19	22955	8.121	778.4	33.9	33.1
2	M30 Concrete	M30	11/05/2018	08/06/2018	150.35 X 150.97 X 149.82	22698	7.974	733.1	32.3	
3	M30 Concrete	M30	11/05/2018	08/06/2018	149.18 X 151.70 X 150.92	22632	8.169	748.6	33.1	

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

Assistant Executive Engineer
Vidyaranyapura Sub Divisio
BBMP, Bangalore - 97

CIVIL Pro Sig Date BANGALORE

Page 1/1
****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2018-04-19-03** **Date: 24/04/2018**

Customer : Assistant Executive Engineer, Vidyaranyapura Sub Division, Bangalore

Address : Vidyaranyapura Sub Division, Bangalore

Project Name : Package No. 04 (Package consists of 28 works)

Agency : M/s. Ram and company, Sri. C R GIRISH, No. 12, Patel Pillegowda layout, Ramachandrapura, Bangalore- 560013

Customer's Reference : BBMP/EE/BTP/WO/129/2017-18

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 19-04-18

Sample ID No : 2018-04-19-03 /01

Customer ID : M30 Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M30 / 7 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 24/04/2018

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	M30 Concrete	M30	17/04/2018	24/04/2018	150.35 X 149.32 X 149.04	22450	8.055	570.4	25.4	25.5
2	M30 Concrete	M30	17/04/2018	24/04/2018	149.42 X 151.19 X 149.22	22591	8.336	603.8	26.7	
3	M30 Concrete	M30	17/04/2018	24/04/2018	150.32 X 150.33 X 150.30	22598	8.258	552.5	24.4	

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

Assistant Executive Engineer
Vidyaranyapura Sub Division
BBMP, Bangalore - 97

CIVIL PRO Sig..... Date..... BANGALORE

Page 1/1
****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2018-04-19-03** **Date: 15/05/2018**

Customer : Assistant Executive Engineer, Vidyaranyapura Sub Division, Bangalore

Address : Vidyaranyapura Sub Division, Bangalore

Project Name : Pacakage No. 04 (Package consists of 28 works)

Agency : M/s. Ram and company, Sri. C R GIRISH, No. 12, Patel Pillegowda layout, Ramachandrapura, Bangalore-560013

Customer's Reference : BBMP/EE/BTP/WO/129/2017-18

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 19-04-18

Sample ID No : 2018-04-19-03 /02

Customer ID : M30 Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M30 / 28 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 15/05/2018

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	M30 Concrete	M30	17/04/2018	15/05/2018	150.17 X 150.13 X 150.54	22544	8.248	747.0	33.1	32.8
2	M30 Concrete	M30	17/04/2018	15/05/2018	150.40 X 151.24 X 149.99	22746	8.375	727.9	32.0	
3	M30 Concrete	M30	17/04/2018	15/05/2018	149.72 X 149.17 X 150.96	22333	8.208	742.6	33.2	

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

CIVIL Pro Sig..... Date..... BANGALORE

Assistant Executive Engineer
Vidyaranyapura Sub Division
BBMP, Bangalore - 97

****End of Report****

CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3
Certificate No.: TC- 5548

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2018-04-23-08** **Date: 27/04/2018**

Customer : Assistant Executive Engineer, Vidyaranyapura Sub Division, Bangalore

Address : Vidyaranyapura Sub Division, Bangalore

Project Name : Package No. 04 (Package consists of 28 works)

Agency : M/s. Ram and company, Sri. C R GIRISH, No. 12, Patel Pillegowda layout, Ramachandrapura, Bangalore- 560013

Customer's Reference : BBMP/EE/BTP/WO/129/2017-18

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 23-04-18

Sample ID No : 2018-04-23-08 /01

Customer ID : M30 Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M30 / 7 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 27/04/2018

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	M30 Concrete	M30	20/04/2018	27/04/2018	149.77 X 149.48 X 150.16	22387	8.325	572.1	25.6	25.5
2	M30 Concrete	M30	20/04/2018	27/04/2018	149.07 X 149.11 X 149.98	22228	8.221	596.6	26.8	
3	M30 Concrete	M30	20/04/2018	27/04/2018	151.89 X 149.74 X 149.82	22745	8.397	550.2	24.2	

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

Assistant Executive Engineer
Vidyaranyapura Sub Division
BBMP, Bangalore - 97

CIVIL Pro Sig..... Date..... BANGALORE

Page 1/1
****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2018-04-23-08** **Date: 18/05/2018**

Customer : Assistant Executive Engineer, Vidyaranyapura Sub Division, Bangalore

Address : Vidyaranyapura Sub Division, Bangalore

Project Name : Pacakage No. 04 (Package consists of 28 works)

Agency : M/s. Ram and company, Sri. C R GIRISH, No. 12, Patel Pillegowda layout, Ramachandrapura, Bangalore-560013

Customer's Reference : BBMP/EE/BTP/WO/129/2017-18

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 23-04-18

Sample ID No : 2018-04-23-08 /02

Customer ID : M30 Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M30 / 28 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 18/05/2018

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	M30 Concrete	M30	20/04/2018	18/05/2018	150.95 X 150.90 X 149.30	22779	8.349	755.3	33.2	33.0
2	M30 Concrete	M30	20/04/2018	18/05/2018	151.07 X 150.14 X 151.16	22682	8.581	741.0	32.7	
3	M30 Concrete	M30	20/04/2018	18/05/2018	150.47 X 150.21 X 150.18	22602	8.347	748.7	33.1	

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

Assistant Executive Engineer
Vidyaranyapura Sub Divisic
BBMP, Bangalore - 97

Page 1/1
****End of Report****

FOR CIVIL Pro.

CIVIL Pro Sig..... Date..... BANGALORE

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2018-05-05-05** **Date: 10/05/2018**

Customer : Assistant Executive Engineer, Vidyaranyapura Sub Division, Bangalore

Address : Vidyaranyapura Sub Division, Bangalore

Project Name : Package No. 04 (Package consists of 28 works)

Agency : M/s. Ram and company, Sri. C R GIRISH, No. 12, Patel Pillegowda layout, Ramachandrapura, Bangalore- 560013

Customer's Reference : BBMP/EE/BTP/WO/129/2017-18

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 05-05-18

Sample ID No : 2018-05-05-05 /01

Customer ID : M30 Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M30 / 7 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 10/05/2018

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	M30 Concrete	M30	03/05/2018	10/05/2018	151.12 X 151.24 X 151.55	22856	8.319	575.6	25.2	25.6
2	M30 Concrete	M30	03/05/2018	10/05/2018	149.44 X 151.25 X 149.54	22602	8.091	608.4	26.9	
3	M30 Concrete	M30	03/05/2018	10/05/2018	149.22 X 151.55 X 151.11	22615	8.274	557.8	24.7	

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

Assistant Executive Engineer
Vidyaranyapura Sub Division
BBMP, Bangalore - 97

CIVIL Pro Sig..... Date..... BANGALORE

Page 1/1
****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2018-05-05-05** **Date: 31/05/2018**

Customer : Assistant Executive Engineer, Vidyaranyapura Sub Division, Bangalore

Address : Vidyaranyapura Sub Division, Bangalore

Project Name : Pacakage No. 04 (Package consists of 28 works)

Agency : M/s. Ram and company, Sri. C R GIRISH, No. 12, Patel Pillegowda layout, Ramachandrapura, Bangalore-560013

Customer's Reference : BBMP/EE/BTP/WO/129/2017-18

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 05-05-18

Sample ID No : 2018-05-05-05 /02

Customer ID : M30 Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M30 / 28 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 31/05/2018

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	M30 Concrete	M30	03/05/2018	31/05/2018	151.45 X 149.90 X 149.60	22703	8.194	768.6	33.9	33.1
2	M30 Concrete	M30	03/05/2018	31/05/2018	151.08 X 151.96 X 149.46	22958	8.190	735.5	32.0	
3	M30 Concrete	M30	03/05/2018	31/05/2018	149.38 X 150.75 X 151.33	22519	8.258	750.7	33.3	

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

Assistant Executive Engineer
Vidyaranyapura Sub Division
BBMP, Bangalore - 97

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

CIVIL PRO * Sig..... Date..... * BANGALORE

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL | GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID	:	**CP-2018-05-07-07** **Date: 11/05/2018**
Customer	:	Assistant Executive Engineer, Vidyaranyapura Sub Division, Bangalore
Address	:	Vidyaranyapura Sub Division, Bangalore
Project Name	:	Package No. 04 (Package consists of 28 works)
Agency	:	M/s. Ram and company, Sri. C R GIRISH, No. 12, Patel Pillegowda layout, Ramachandrapura, Bangalore- 560013
Customer's Reference	:	BBMP/EE/BTP/WO/129/2017-18
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	07-05-18
Sample ID No	:	2018-05-07-07 /01
Customer ID	:	M30 Concrete
Sample Type /Size	:	150X150X150 mm
Sample grade/Age	:	M30 / 7 Days Compressive Strength
Reference to BIS codes	:	IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5
Date of test	:	11/05/2018

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	M30 Concrete	M30	04/05/2018	11/05/2018	149.15 X 150.35 X 149.21	22424	8.376	564.0	25.2	25.4
2	M30 Concrete	M30	04/05/2018	11/05/2018	150.03 X 150.60 X 151.01	22594	8.285	595.0	26.3	
3	M30 Concrete	M30	04/05/2018	11/05/2018	150.14 X 151.69 X 151.37	22775	8.150	562.9	24.7	

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

Assistant Executive Engineer
Vidyaranyapura Sub Division
BBMP, Bangalore - 97

CIVIL PRO Sig..... Date..... BANGALORE

****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID	:	**CP-2018-05-07-07** **Date: 01/06/2018**
Customer	:	Assistant Executive Engineer, Vidyaranyapura Sub Division, Bangalore
Address	:	Vidyaranyapura Sub Division, Bangalore
Project Name	:	Pacakage No. 04 (Package consists of 28 works)
Agency	:	M/s. Ram and company, Sri. C R GIRISH, No. 12, Patel Pillegowda layout, Ramachandrapura, Bangalore-560013
Customer's Reference	:	BBMP/EE/BTP/WO/129/2017-18
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	07-05-18
Sample ID No	:	2018-05-07-07 /02
Customer ID	:	M30 Concrete
Sample Type /Size	:	150X150X150 mm
Sample grade/Age	:	M30 / 28 Days Compressive Strength
Reference to BIS codes	:	IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5
Date of test	:	01/06/2018

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	M30 Concrete	M30	04/05/2018	01/06/2018	151.82 X 151.63 X 149.86	23021	8.391	767.4	33.3	33.3
2	M30 Concrete	M30	04/05/2018	01/06/2018	149.54 X 149.05 X 151.16	22289	8.103	731.0	32.8	
3	M30 Concrete	M30	04/05/2018	01/06/2018	150.46 X 151.44 X 150.64	22785	8.484	769.1	33.8	

Note:
The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

CIVIL PRO Sig..... Date..... BANGALORE

Assistant Executive Engineer
Vidyaranyapura Sub Divisio-
BBMP, Bangalore - 97

****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2018-05-08-04** **Date: 12/05/2018**

Customer : Assistant Executive Engineer, Vidyaranyapura Sub Division, Bangalore

Address : Vidyaranyapura Sub Division, Bangalore

Project Name : Package No. 04 (Package consists of 28 works)

Agency : M/s. Ram and company, Sri. C R GIRISH, No. 12, Patel Pillegowda layout, Ramachandrapura, Bangalore- 560013

Customer's Reference : BBMP/EE/BTP/WO/129/2017-18

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 08-05-18

Sample ID No : 2018-05-08-04 /01

Customer ID : M30 Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M30 / 7 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 12/05/2018

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	M30 Concrete	M30	05/05/2018	12/05/2018	151.98 X 150.23 X 150.40	22831	8.237	584.5	25.6	25.8
2	M30 Concrete	M30	05/05/2018	12/05/2018	149.42 X 149.53 X 151.25	22342	8.258	602.7	27.0	
3	M30 Concrete	M30	05/05/2018	12/05/2018	151.11 X 149.51 X 149.03	22592	8.474	560.5	24.8	

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

Assistant Executive Engineer
Vidyaranyapura Sub Division
BBMP, Bangalore - 97

Page 1/1
****End of Report****

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2018-05-08-04** **Date: 02/06/2018**

Customer : Assistant Executive Engineer, Vidyaranyapura Sub Division, Bangalore

Address : Vidyaranyapura Sub Division, Bangalore

Project Name : Pacakage No. 04 (Package consists of 28 works)

Agency : M/s. Ram and company, Sri. C R GIRISH, No. 12, Patel Pillegowda layout, Ramachandrapura, Bangalore-560013

Customer's Reference : BBMP/EE/BTP/WO/129/2017-18

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 08-05-18

Sample ID No : 2018-05-08-04 /02

Customer ID : M30 Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M30 / 28 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 02/06/2018

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	M30 Concrete	M30	05/05/2018	02/06/2018	149.77 X 149.94 X 151.83	22457	8.386	753.4	33.5	33.3
2	M30 Concrete	M30	05/05/2018	02/06/2018	151.10 X 150.49 X 149.04	22739	8.174	746.0	32.8	
3	M30 Concrete	M30	05/05/2018	02/06/2018	150.17 X 149.85 X 151.62	22504	8.123	754.6	33.5	

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

Assistant Executive Engineer
Vidyaranyapura Sub Division
BBMP, Bangalore - 97

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

CIVIL Pro Sig..... Date..... BANGALORE

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID	:	**CP-2018-05-16-04** **Date: 21/05/2018**
Customer	:	Assistant Executive Engineer, Vidyaranyapura Sub Division, Bangalore
Address	:	Vidyaranyapura Sub Division, Bangalore
Project Name	:	Package No. 04 (Package consists of 28 works)
Agency	:	M/s. Ram and company, Sri. C R GIRISH, No. 12, Patel Pillegowda layout, Ramachandrapura, Bangalore- 560013
Customer's Reference	:	BBMP/EE/BTP/WO/129/2017-18
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	16-05-18
Sample ID No	:	2018-05-16-04 /01
Customer ID	:	M30 Concrete
Sample Type /Size	:	150X150X150 mm
Sample grade/Age	:	M30 / 7 Days Compressive Strength
Reference to BIS codes	:	IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5
Date of test	:	21/05/2018

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	M30 Concrete	M30	14/05/2018	21/05/2018	151.28 X 150.77 X 150.57	22809	8.377	587.1	25.7	25.7
2	M30 Concrete	M30	14/05/2018	21/05/2018	149.06 X 151.50 X 149.25	22582	8.579	603.2	26.7	
3	M30 Concrete	M30	14/05/2018	21/05/2018	150.62 X 150.50 X 150.56	22668	8.493	555.5	24.5	

Note:
The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

Assistant Executive Engineer
Vidyaranyapura Sub Division
BBMP, Bangalore - 97

Page 1/1
****End of Report****

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.
R KARTHIK RECHAN
Authorized Signatory
Quality Manager

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2018-05-16-04** **Date: 11/06/2018**

Customer : Assistant Executive Engineer, Vidyaranyapura Sub Division, Bangalore

Address : Vidyaranyapura Sub Division, Bangalore

Project Name : Pacakage No. 04 (Package consists of 28 works)

Agency : M/s. Ram and company, Sri. C R GIRISH, No. 12, Patel Pillegowda layout, Ramachandrapura, Bangalore-560013

Customer's Reference : BBMP/EE/BTP/WO/129/2017-18

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 16-05-18

Sample ID No : 2018-05-16-04 /02

Customer ID : M30 Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M30 / 28 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 11/06/2018

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	M30 Concrete	M30	14/05/2018	11/06/2018	149.77 X 151.34 X 150.51	22666	8.103	767.2	33.8	33.5
2	M30 Concrete	M30	14/05/2018	11/06/2018	151.38 X 151.32 X 149.13	22906	8.408	754.6	32.9	
3	M30 Concrete	M30	14/05/2018	11/06/2018	151.53 X 150.93 X 150.02	22871	8.419	770.1	33.7	

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

Assistant Executive Engineer
Vidyaranyapura Sub Division
BBMP, Bangalore - 97

CIVIL Pro Sig..... Date..... BANGALORE

****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2018-05-17-04** **Date: 22/05/2018**

Customer : Assistant Executive Engineer, Vidyaranyapura Sub Division, Bangalore

Address : Vidyaranyapura Sub Division, Bangalore

Project Name : Package No. 04 (Package consists of 28 works)

Agency : M/s. Ram and company, Sri. C R GIRISH, No. 12, Patel Pillegowda layout, Ramachandrapura, Bangalore- 560013

Customer's Reference : BBMP/EE/BTP/WO/129/2017-18

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 17-05-18

Sample ID No : 2018-05-17-04 /01

Customer ID : M30 Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M30 / 7 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 22/05/2018

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	M30 Concrete	M30	15/05/2018	22/05/2018	149.81 X 149.88 X 150.27	22454	8.368	573.7	25.6	25.4
2	M30 Concrete	M30	15/05/2018	22/05/2018	151.75 X 149.78 X 150.86	22728	8.130	598.8	26.3	
3	M30 Concrete	M30	15/05/2018	22/05/2018	151.67 X 149.30 X 149.02	22644	8.235	551.4	24.4	

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

Assistant Executive Engineer
Vidyaranyapura Sub Division
BBMP, Bangalore - 97

CIVIL PRO Sig..... Date..... BANGALORE

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL |
GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2018-05-17-04** **Date: 12/06/2018**

Customer : Assistant Executive Engineer, Vidyaranyapura Sub Division, Bangalore

Address : Vidyaranyapura Sub Division, Bangalore

Project Name : Pacakage No. 04 (Package consists of 28 works)

Agency : M/s. Ram and company, Sri. C R GIRISH, No. 12, Patel Pillegowda layout, Ramachandrapura, Bangalore-560013

Customer's Reference : BBMP/EE/BTP/WO/129/2017-18

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 17-05-18

Sample ID No : 2018-05-17-04 /02

Customer ID : M30 Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M30 / 28 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 12/06/2018

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	M30 Concrete	M30	15/05/2018	12/06/2018	151.09 X 151.32 X 150.34	22864	8.380	771.1	33.7	33.2
2	M30 Concrete	M30	15/05/2018	12/06/2018	149.51 X 151.93 X 151.26	22716	8.260	739.2	32.5	
3	M30 Concrete	M30	15/05/2018	12/06/2018	151.23 X 151.58 X 151.11	22924	8.206	762.0	33.2	

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

Assistant Executive Engineer
Vidyaranyapura Sub Divisio
BBMP, Bangalore - 97

CIVIL Pro Sig..... Date..... BANGALORE

****End of Report****

M : 9972924626 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL |
GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2018-05-21-04** **Date: 25/05/2018**

Customer : Assistant Executive Engineer, Vidyaranyapura Sub Division, Bangalore

Address : Vidyaranyapura Sub Division, Bangalore

Project Name : Package No. 04 (Package consists of 28 works)

Agency : M/s. Ram and company, Sri. C R GIRISH, No. 12, Patel Pillegowda layout, Ramachandrapura, Bangalore- 560013

Customer's Reference : BBMP/EE/BTP/WO/129/2017-18

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 21-05-18

Sample ID No : 2018-05-21-04 /01

Customer ID : M30 Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M30 / 7 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 25/05/2018

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	M30 Concrete	M30	18/05/2018	25/05/2018	150.09 X 150.47 X 150.56	22584	8.235	584.4	25.9	25.8
2	M30 Concrete	M30	18/05/2018	25/05/2018	149.72 X 150.95 X 151.61	22600	8.134	604.9	26.8	
3	M30 Concrete	M30	18/05/2018	25/05/2018	150.85 X 149.93 X 149.48	22616	8.282	561.2	24.8	

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

Assistant Executive Engineer
Vidyaranyapura Sub Divisi
BBMP, Bangalore - 97

Page 1/1
****End of Report****

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2018-05-21-04** **Date: 15/06/2018**

Customer : Assistant Executive Engineer, Vidyaranyapura Sub Division, Bangalore

Address : Vidyaranyapura Sub Division, Bangalore

Project Name : Pacakage No. 04 (Package consists of 28 works)

Agency : M/s. Ram and company, Sri. C R GIRISH, No. 12, Patel Pillegowda layout, Ramachandrapura, Bangalore-560013

Customer's Reference : BBMP/EE/BTP/WO/129/2017-18

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 21-05-18

Sample ID No : 2018-05-21-04 /02

Customer ID : M30 Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M30 / 28 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 15/06/2018

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	M30 Concrete	M30	18/05/2018	15/06/2018	150.00 X 149.09 X 151.56	22362	7.986	746.5	33.4	33.3
2	M30 Concrete	M30	18/05/2018	15/06/2018	151.01 X 151.96 X 150.79	22947	8.329	749.4	32.7	
3	M30 Concrete	M30	18/05/2018	15/06/2018	151.07 X 149.82 X 151.05	22633	8.108	764.0	33.8	

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

Assistant Executive Engineer
Vidyaranyapura Sub Division
BBMP, Bangalore - 97

Page 1/1
****End of Report****

CIVIL PRO Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager